



*live inspired*

# LASTRICATO

GLAZED PORCELAIN TILE



**3Y79 Surbo BI**  
12"x18"  
**3Y82 Surbo BI**  
12"x12"  
**3Y85 Surbo BI**  
5<sup>7/8</sup>"x12"  
**3Y88 Surbo BI**  
5<sup>7/8</sup>"x5<sup>7/8</sup>"  
**3Y91 Surbo BI**  
3<sup>7/8</sup>"x3<sup>7/8</sup>"



**3Y77 Trani BG**  
12"x18"  
**3Y80 Trani BG**  
12"x12"  
**3Y83 Trani BG**  
5<sup>7/8</sup>"x12"  
**3Y86 Trani BG**  
5<sup>7/8</sup>"x5<sup>7/8</sup>"  
**3Y89 Trani BG**  
3<sup>7/8</sup>"x3<sup>7/8</sup>"



**3Y78 Borriol BR**  
12"x18"  
**3Y81 Borriol BR**  
12"x12"  
**3Y84 Borriol BR**  
5<sup>7/8</sup>"x12"  
**3Y87 Borriol BR**  
5<sup>7/8</sup>"x5<sup>7/8</sup>"  
**3Y90 Borriol BR**  
3<sup>7/8</sup>"x3<sup>7/8</sup>"



**2X54 Porfido GR**  
12"x18"  
**2X51 Porfido GR**  
12"x12"  
**2X57 Porfido GR**  
5<sup>7/8</sup>"x12"  
**2X60 Porfido GR**  
5<sup>7/8</sup>"x5<sup>7/8</sup>"  
**2X80 Porfido GR**  
3<sup>7/8</sup>"x3<sup>7/8</sup>"



**2X52 Porfido RS**  
12"x18"  
**2X49 Porfido RS**  
12"x12"  
**2X55 Porfido RS**  
5<sup>7/8</sup>"x12"  
**2X58 Porfido RS**  
5<sup>7/8</sup>"x5<sup>7/8</sup>"  
**2X78 Porfido RS**  
3<sup>7/8</sup>"x3<sup>7/8</sup>"



**2X53 Basalto NE**  
12"x18"  
**2X50 Basalto NE**  
12"x12"  
**2X56 Basalto NE**  
5<sup>7/8</sup>"x12"  
**2X59 Basalto NE**  
5<sup>7/8</sup>"x5<sup>7/8</sup>"  
**2X79 Basalto NE**  
3<sup>7/8</sup>"x3<sup>7/8</sup>"

-  Floor Tile
-  Wall Tile
-  Suitable for Outdoors
-  Slight Variation
-  Frost Resistant
-  Meets ADA Recommendations
-  Abrasion Resistance
-  C.O.F. (Wet)
-  C.O.F. (Dry)
-  Certified No VOC



## TECHNICAL SPECIFICATIONS

DESCRIPTION	ANSI STANDARD	RESULT	ASTM TEST METHOD	
Water Absorption	≤ 0.50%	≤ 0.50%	C373	
Frost Resistance	As Reported	Resistant	C1026	
Scratch Resistance	MOHS 1-10	8	MOHS SCALE	
Breaking Strength	12"x18"	≥ 250 lbf.	≥ 500 lbf.	C648
	12"x12"	≥ 250 lbf.	≥ 655 lbf.	C648
Facial Dimension	-3.0 % < Nominal ≤ 3.0 %	Within Standard	C499	
Thickness	≤ 0.04 in (1.02 mm max)	Within Standard	C499	
Wedging (Squareness)	+/- 0.50 % or +/- 2.0 mm*	Within Standard	C502	
Warpage (Flatness)	+/- 0.75 % or +/- 2.3 mm*	Within Standard	C485	
Abrasion Resistance	Class 0 - Class V	Class IV	C1027	
C.O.F. (Wet)	As Reported	0.60 ≤ COF < 0.70	C1028	
C.O.F. (Dry)	As Reported	0.80 ≤ COF < 0.90	C1028	
Chemical Resistance	Class A - Class E	Class A	C650	
Stain Resistance	Class A - Class E	Class A	C1378	

\* Whichever is less

