


live inspired



# REVISION


COLOR BODY PORCELAIN TILE | RECTIFIED



**R4P3** Revision BI  
24"x24" Rectified  
**R4Q3** Revision BI  
12"x24" Rectified  
**R4P8** Revision BI  
12"x48" Rectified



**R5P4** Revision BI  
Mosaic  
12"x24"



**R4P4** Revision BG  
24"x24" Rectified  
**R4Q4** Revision BG  
12"x24" Rectified  
**R4P9** Revision BG  
12"x48" Rectified



**R5P5** Revision BG  
Mosaic  
12"x24"



**R4P6** Revision RS  
24"x24" Rectified  
**R4Q6** Revision RS  
12"x24" Rectified  
**R4Q1** Revision RS  
12"x48" Rectified




**R5P7** Revision RS  
Mosaic  
12"x24"



**R4P5** Revision MA  
24"x24" Rectified  
**R4Q5** Revision MA  
12"x24" Rectified  
**R4Q0** Revision MA  
12"x48" Rectified



**R5P6** Revision MA  
Mosaic  
12"x24"



**R4P7** Revision NE  
24"x24" Rectified  
**R4Q7** Revision NE  
12"x24" Rectified  
**R4Q2** Revision NE  
12"x48" Rectified



**R5P8** Revision NE  
Mosaic  
12"x24"



**R5P1** Nest BI  
Insert  
12"x48"



**R5P2** Nest MA  
Insert  
12"x48"



**R5P3** Nest NE  
Insert  
12"x48"

TRIMS



**R4W8** Revision BI Bullnose  
**R4W9** Revision BG Bullnose  
**R4X1** Revision RS Bullnose  
**R4X0** Revision MA Bullnose  
**R4X2** Revision NE Bullnose  
4"x24"

- Floor Tile
- Wall Tile
- Modular Tile
- Rectified Tile
- Decorative Tile
- Trim Available
- Uniform Appearance
- Frost Resistant
- Abrasion Resistance
- C.O.F. (Wet)
- C.O.F. (Dry)
- 45% Minimum Pre-Consumer Recycled Content
- Certified No VOC



Contributes to LEED Credits

## TECHNICAL SPECIFICATIONS

DESCRIPTION	ANSI STANDARD	RESULT	ASTM TEST METHOD
Water Absorption	≤ 0.50%	≤ 0.50%	C373
Frost Resistance	As Reported	Resistant	C1026
Scratch Resistance	MOHS 1-10	6	MOHS SCALE
Breaking Strength	12"x24"	≥ 250 lbf.	≥ 995 lbf. C648
	12"x48"	≥ 250 lbf.	≥ 1450 lbf. C648
	24"x24"	≥ 250 lbf.	≥ 995 lbf. C648
Facial Dimension	-3.0 % < Nominal ≤ 2.0 %	Within Standard	C499
Thickness	≤ 0.04 in (1.02 mm max)	Within Standard	C499
Wedging (Squareness)	+/- 0.25 % or +/- 0.8 mm*	Within Standard	C502
Warpage (Flatness)	+/- 0.40 % or +/- 1.3 mm*	Within Standard	C485
Abrasion Resistance	Class 0 - Class V	Class III	C1027
C.O.F. (Wet)	As Reported	0.30 ≤ COF < 0.40	C1028
C.O.F. (Dry)	As Reported	0.60 ≤ COF < 0.70	C1028
Chemical Resistance	Class A - Class E	Class A	C650
Stain Resistance	Class A - Class E	Class A	C1378

\* Whichever is less

