

RAGNO  USA

VESTA GLAZED PORCELAIN TILE | 3D PRINTING TECHNIQUE | MADE IN THE USA



live inspired





live inspired

VESTA

GLAZED PORCELAIN TILE | 3D PRINTING TECHNIQUE | MADE IN THE USA



AL6H Vesta GR
20"x20"
AL8C Vesta GR
12"x24"
AL6E Vesta GR
13"x13"
AL6B Vesta GR
6 1/2"x6 1/2"



AL6J Vesta IV
20"x20"
AL8D Vesta IV
12"x24"
AL6F Vesta IV
13"x13"
AL6C Vesta IV
6 1/2"x6 1/2"



AL6K Vesta NO
20"x20"
AL8E Vesta NO
12"x24"
AL6G Vesta NO
13"x13"
AL6D Vesta NO
6 1/2"x6 1/2"



AL7U Vesta GR
Listelli
1 3/8"x13"



AL84 Vesta GR
Mosaic - Square 2"x2"
13"x13"



AL7V Vesta IV
Listelli
1 3/8"x13"



AL85 Vesta IV
Mosaic - Square 2"x2"
13"x13"



AL7W Vesta NO
Listelli
1 3/8"x13"



AL86 Vesta NO
Mosaic - Square 2"x2"
13"x13"



AL36 Grecian Metallic
Deco
2"x13"

TRIMS



AL6L Vesta GR Bullnose
AL6M Vesta IV Bullnose
AL6N Vesta NO Bullnose
3"x13"

-  Floor Tile
-  Wall Tile
-  Modular Tile
-  3d Printing Technique
-  Decorative Tile
-  Trim Available
-  Substantial Variation
-  Frost Resistant
-  Abrasion Resistance
-  C.O.F. (Wet)
-  C.O.F. (Dry)
-  21% Minimum Pre-Consumer Recycled Content
-  Certified No VOC



Contributes to LEED Credits

TECHNICAL SPECIFICATIONS

DESCRIPTION	ANSI STANDARD	RESULT	ASTM TEST METHOD	
Water Absorption	≤ 0.50%	≤ 0.50%	C373	
Frost Resistance	As Reported	Resistant	C1026	
Scratch Resistance	MOHS 1-10	6	MOHS SCALE	
Breaking Strength	20"x20"	≥ 250 lbf.	≥ 776 lbf.	C648
	13"x13"	≥ 250 lbf.	≥ 500 lbf.	C648
Facial Dimension	-3.0 % < Nominal ≤ 3.0 %	Within Standard	C499	
Thickness	≤ 0.04 in (1.02 mm max)	Within Standard	C499	
Wedging (Squareness)	+/- 0.50 % or +/- 2.0 mm*	Within Standard	C502	
Warpage (Flatness)	+/- 0.75 % or +/- 2.3 mm*	Within Standard	C485	
Abrasion Resistance	Class 0 - Class V	Class IV	C1027	
C.O.F. (Wet)	As Reported	0.70 ≤ COF < 0.80	C1028	
C.O.F. (Dry)	As Reported	0.50 ≤ COF < 0.60	C1028	
Chemical Resistance	Class A - Class E	Class B	C650	
Stain Resistance	Class A - Class E	Class A	C1378	

* Whichever is less

